OpuLith









Book-match



126"x60"



Book-match



126"x60"



Book-match



126"x60"



Book-match



Tile Applications: Usage

Floors

Walls

Counter-tops

126"x60"



126"x60"



Thickness:

12 mm

126"x60"

STANDARD VALUE Water Absorption C373 Impervious < 0.5% < 0.1% Thickness Dimension C499 Range ± 0.02 Inc. Max. ≤± 0.02 **I**nc. Facial Dimension (Length/Width Variation) C499 ± 0.25% ≤± 0.25% Wedging C502 \pm 0.25% ≤± 0.25% C482 ≥ 150 psi ≥ 200 psi Dry Bond Strength Breaking Strength C648 ≥ 175 **I**b. ≥ 200 **l**b. Scratch Test Hardness (MOHS) Range 0 - 10 ≥ 7 (No Regu**l**ation) Impervious (Porcelain) Class P1: ≤ 175 mm C1243 ≤ 175 mm Deep Abrasion Resistance No sample must show alterations to the surfaces No evidence C1026 Frost Resistance of damage Robinson Test AC627 As reported Extra Heavy No Requirement Range E – A Chemical Resistance C650 Class A No Requirement Range E — A Stain Resistance C1378 Class A* DCOF (Coefficient of Friction) BOT 3000 ≥ 0.42* ≥0.42 - ≤0.60* Visual Evaluation Shade & Texture No Requirement Range V0 – V4 V1 – V3 Aesthetic Classification 10 to 80 depending on style/color selection No Requirement Range 0 -100 LRV (Light Reflectance Value) C609

Variations in shade and color, and sometimes in texture, are inherent in all file products such as porcelain, glass and ceramic. This variation can be present from piece to piece within any production run. Prior to any installation, several loose files should be arranged and approved by the customer.

Light Commercial

Commercial

Residentia

^{*}All values are given for Matte or Honed material. No values are given for Polished material. We do not recommend polished surfaces in the areas subject to exposure from grease, oil or water. For level interior spaces to be walked upon when wet see ANSI A 137.1 section 6.2.2.1,10 – Section 9.6 for test procedures.